

PRODUCT INFORMATION



AGS 3506 COLOUR

Art. No: 3506/xx

Graffiti Protection for Exterior and interior for hard & porous surfaces



AGS 3506 COLOUR is a pigmented water-carried all-weather long-term protection, formulated for most types of surfaces. Protects against graffiti from spray paint or marker/felt-tip pen. Protects against graffiti, airborne pollution and moisture for a minimum of 5 years. Permeable and allows protected surface to breath. Prevents graffiti from penetrating into substrate. A so called sacrificial protection, which means that surface must be re-protected, following graffiti removal. AGS 3506 is readily biodegradable.

AGS 3506 COLOUR is a pigmented water based all-weather long-term protection, formulated for most types of surfaces. **AGS 3506 COLOUR** can be pigmented according to NCS and RAL standards.

[See Standard Colours.](#)

NB! Fresh concrete has to cure for at least 28 days before protection.

INSTRUCTIONS FOR USE:

Preparation

Clean off both graffiti and other contamination, such as traffic dirt, wax, oil and paint-residue etc. from substrate. Mask and protect windows in a suitable manner. Ideal temperature for external application should be between 10-35°C. Minimum temperature is +5°C. Relative humidity must not exceed 95%.

Exterior protection

Shake or stir product well prior to use. **AGS 3506** can be applied with an airless spray, brush or roller. The protection is applied 2-3 times.

Note! Allow some intermediate drying.

AGS 3506 can be applied to a damp, not wet, surface.

Runs and/or excessive application can easily be washed off with water, following completion of work.

Interior protection

Painted substrate can be protected using a squeegee brush, roller or with low-pressure spray in combination with a squeegee. The protection is applied three times.

Exterior Graffiti removal

Method 1 - Normal substrate

Remove graffiti with hot water and high-pressure (90°C & 90-150 bar / 1300-2175 PSI). In difficult cases, AGS graffiti removers are used in conventional manner. Re-protect cleaned area.

Method 2 - delicate substrate

Apply **AGS 3505** with a low-pressure sprayer. Allow a few minutes for the solvent remover to act and then rinse off with hot water (60-90°C & 60-80 bar/870-1160 PSI). The method is most suitable when substrate is brittle. Any graffiti left on the surface can be removed with **AGS 3505** on a cloth. The cleaned area should be wiped with a cloth and water. Re-protect cleaned area.

Interior Graffiti removal

Painted substrate: Dampen the area with **AGS 3505** and wipe off graffiti with white nylon cloth or rag. If possible use high-pressure hot water and wet-vac machines.

Porous substrate: Rinse off with hot water and wet-vac.

Re-protection of cleaned surface

When removing graffiti, the protective coating is also normally removed. Re-protect 2-3 times with **AGS 3502**.

Dosage

Use in concentrated form.

Modified: 2007-12-21

This product information is intended as a guide for use of this product. TRION TENSID AB cannot give any guarantee for end result achieved. Applicator of product shall carry out testing and be responsible for the result.

TRION TENSID AB

Svederusgatan 1-3 | SE-754 50 UPPSALA | SWEDEN Tel: +46 18-15 61 90 Fax: +46 18-69 66 27

Email: info@trion.se Homepage: www.trion.se

AGS 3506 COLOUR Graffiti Protection

Consumption

Varies dependent upon type of surface material. It's porosity and capillary etc.

Guidelines

- Concrete, brick or similar 0,10-0,15 ltr/m²/coat.
- Sandstone, plaster or other soft absorbent surfaces 0,15-0,20 ltr/m²/ coat.

Drying-period

The protected surface will be water- and graffiti-resistant after 2 hours and dry after 4 hours. Ultimate protective effect will be achieved after 72 hours.

Appearance on surface

Transparent, mostly invisible dependent on type of surface. UV-resistant. Weather-, water-, and graffiti - resistant.

Technical data

- Coloured water-carried wax dispersion.
- Supplied in 10 litres plastic jig.
- Specific weight, 1,1 kg/litre.
- Odourless.
- pH-value approx. 8.
- Solid contents 16,5%

Precautions

Use protective clothing and gloves.

Marking

Not classified as dangerous.
Not classified in ADR or IMDG.

Storage

Store frost-free in closed original container.

Shelf life

Approximately 12 months in unopened container.

Modified: 2007-12-21

This product information is intended as a guide for use of this product. TRION TENSID AB cannot give any guarantee for end result achieved. Applicator of product shall carry out testing and be responsible for the result.

TRION TENSID AB

Svederusgatan 1-3 | SE-754 50 UPPSALA | SWEDEN Tel: +46 18-15 61 90 Fax: +46 18-69 66 27
Email: info@trion.se Homepage: www.trion.se