

PRODUCT INFORMATION



AGS 3513

Art. No: 3513
Shiny protective coating
for hard & porous surfaces



A water-carried all-weather long term protection, formulated for hard surfaces. Provides extra strong protection against spray paint, marker/felt-tip pens and mechanical damage. Protects against airborne pollution and moisture for a minimum of 5 years. Correctly applied, life expectancy against graffiti is approximately 5 years. Prevents graffiti from penetrating into substrate.

A so called sacrificial protection, which means that surface must be re protected, following graffiti removal. AGS 3513 is biodegradable. (Same as AGS 3512 but surface gets more shiny.)

INSTRUCTIONS FOR USE:

Preparation

Clean off both graffiti and other contamination, such as traffic dirt, wax, oil and paint-residue etc. from substrate. Mask and protect windows in a suitable manner. Ideal temperature for external application should be between 10-35°C. Minimum temperature is +5°C. Relative humidity must not exceed 95%.

Exterior protection

Shake or stir product well prior to use. **AGS 3513** can be applied with a sponge, low-pressure sprayer or a airless spray gun. The protection is applied in 3-4 thin layers. *Note! Allow some intermediate drying.* Runs and/or excessive application can easily be rinsed off with water, following completion of work.

Interior protection

Painted substrate can be protected using a sponge, squeegee brush, roller or with low-pressure spray in combination with a squeegee. The protection is preferably applied in 3-4 thin layers.

Exterior Graffiti removal

Method 1 - Normal shiny substrate

Remove graffiti with high-pressure hot water (90°C & 90-150 bar / 1300-2175 PSI). In difficult cases, AGS graffiti removers are used in conventional manner. Re-protect cleaned area.

Method 2 - delicate shiny substrate

Apply **AGS 3505** or **AGS 5 SR** with a low-pressure sprayer. Allow a few minutes for the solvent remover to act and then rinse off with hot water (60-90°C & 60-80 bar/870-1160 PSI). The method is most suitable when substrate is brittle. Any graffiti left on the surface can be removed with **AGS 3505** on a cloth. The cleaned area should be wiped with a cloth and neutralised with water. **Re-protect** cleaned area.

Interior Graffiti removal

Painted substrate

Dampen the area with **AGS 3505** and wipe off graffiti with a cloth or rag, neutralise with water. **Re-protect** cleaned area.

Re-protection of cleaned surface

When removing graffiti, the protective coating is also normally removed. Re-protect with 3-4 layers of **AGS 3513**. The surface must prior to re-protection dry up for 30-60 minutes.

Dosage

Use in concentrated form.

Consumption

Varies dependent upon type of surface material and it's porosity.

Modified: 2010-09-16

This product information is intended as a guide for use of this product. TRION TENSID AB cannot give any guarantee for end result achieved. Applicator of product shall carry out testing and be responsible for the result.

TRION TENSID AB

Svederusgatan 1-3 | SE-754 50 UPPSALA | SWEDEN Tel: +46 18-15 61 90 Fax: +46 18-69 66 27
Email: info@trion.se Homepage: www.trion.se

AGS 3513

Graffiti Protection

Guidelines

- 0,10-0,20 litre/m²/totally.

Drying-period

The protected surface will be water- and graffiti-resistant after 2 hours. Fully hardened after 72 hours.

Appearance on surface

Shiny, transparent, mostly invisible dependent on type of surface. UV-resistant. Weather-, water- and graffiti-resistant.

Technical data

- White, water-carried dispersion.
- Supplied in 5 litres. plastic jig.
- Specific weight 1,0 kg/litre.
- Odourless.
- pH-value approx. 8.
- Solid contents 19,0%

Precautions

Use protective clothing and gloves.

Marking

Not classified as dangerous.
Not classified in ADR or IMDG.

Storage

Store frost-free in closed original container.

Shelf life

Approximately 12 months in unopened container.

Modified: 2010-05-31

This product information is intended as a guide for use of this product. TRION TENSID AB cannot give any guarantee for end result achieved. Applicator of product shall carry out testing and be responsible for the result.

TRION TENSID AB

Svederusgatan 1-3 | SE-754 50 UPPSALA | SWEDEN Tel: +46 18-15 61 90 Fax: +46 18-69 66 27
Email: info@trion.se Homepage: www.trion.se